

# SILIKAL® RV 368 resin

Reactive, impact-resistant resin with low-temperature flexibility for self-levelling coatings



Expect more from your floor.

SILIKAL® RV 368 resin is a solvent-free, 2-component methacrylic resin of high impact resistance and low-temperature flexibility whose highly-molecular structure makes it outstandingly suitable for self-levelling coatings subject to extreme stresses, predominantly outdoors or for cold stores. Coatings made from SILIKAL® RV 368 resin are durably elastic and able to crack bridging.

SILIKAL® RV 368 resin is characterized by outstanding impact resistance. Its high elasticity ensures lasting crack bridging, so that substrate movements can be better absorbed. The good low-temperature flexibility improves its behaviour outdoors in the event of changes in climate or load stresses on bridge roadways or in cold stores. Because of the high viscosity, the coarse particles of the filler remains longer in the self-levelling recipe suspension, so that no separation between fine and coarse particles occurs within the flooring (particle homogeneity). This has a further beneficial effect on crack bridging.

When combined with fine filler, SILIKAL® RV 368 resin can also be used as a 1 – 1.5 mm membrane underneath normal flooring systems of SILIKAL® R 61, SILIKAL® R 62 or SILIKAL® RV 368 resin in order to improve impact resistance and crack bridging (tight to liquids).

## Application

SILIKAL® RV 368 resin is used as a binder in manufacturing various coating types and recipes. Indoors it can be coated on the following substrates: concrete, screed, ceramic tiles, asphalt and steel.

Outdoors SILIKAL® RV 368 resin, like all other SILIKAL® resins, must not be laid on asphalt surfaces because otherwise cracks may be expected to form, particularly on large surfaces. The various substrates must be primed in accordance with our general recommendations (see literature on substrates).

## Membrane coat

SILIKAL® RV 368 resin must always be applied to a minimum thickness of 1 mm. Mixtures in a ratio of 2 : 1 to 3 : 1 with SILIKAL® Filler QM have proven to be most suitable. Membrane coats must not be sanded over their full area before being covered with SILIKAL® R 61, SILIKAL® R 62 or SILIKAL® RV 368 resin self-levelling coatings. Membrane coats are advisable e. g. on blasted sheet steel, critical substrates or if there are particular mechanical stresses.

## Main coat

For the main coat, a differentiation must be made between two filler recipes. The finer is used in the manufacture of thinner toppings of 2 – 4 mm, the coarser for thicker coats of 4 – 7 mm. The recommended sand sprinkling of SILIKAL® Filler QS 0.7 – 1.2 mm is absolutely essential, as this ensures the surface straining point stress. Dried basalt chippings or coarse quartz sand is also suitable for sprinkling over areas subject to traffic.

## 1. Scratch slurry

(Use in systems B, C, D, E)

## Guideline recipe and batch quantities

Item	Component	Guideline recipe (% by weight)	Comments	Batch for 30 litre bucket	
1	SILIKAL® RV 368 resin	35 %		13.5 kg	13.5 litres
2	SILIKAL® SL filler	65 %	1 sack	25.0 kg	approx. 18 litres
	<b>Total:</b>	<b>100 %</b>	<b>Average consumption: 1.6 kg/m<sup>2</sup> per mm thickness</b>	<b>38.5 kg</b>	<b>approx. 24 litres</b>
3	SILIKAL® Hardening Powder	1 – 6 % related to item 1	See “Hardener dosages” table for quantities	135 – 810 g	

### Silikal GmbH & Co. KG

✉ Ostring 23  
☎ +49 (0) 61 82 / 92 35-0  
🌐 www.silikal.de

D-63533 Mainhausen  
☎ +49 (0) 61 82 / 92 35-40  
@ mail@silikal.de

### Silikal product information

Issue 2.00.A

July 2006

Data sheet SILIKAL® RV 368

Page 1 of 3

# SILIKAL® RV 368 resin

Reactive, impact-resistant resin with low-temperature flexibility for self-levelling coatings



## 2. Self-levelling coating 2 – 4 mm

(Use in system D or as scratch slurry)

### Guideline recipe and batch quantities

Item	Component	Guideline recipe (% by weight)	Comments	Batch for 30 litre bucket	
1	SILIKAL® RV 368 resin	35 %		14 kg	14 litres
2*	SILIKAL® Filler SV	65 %	1 sack	25 kg	approx. 22 litres
	<b>Total:</b>	<b>100 %</b>	<b>Average consumption: 1.6 kg/m<sup>2</sup> per mm thickness</b>	<b>39 kg</b>	<b>approx. 24 litres</b>
3	SILIKAL® Hardening Powder	1 – 6 % related to item 1	See “Hardener dosages” table for quantities	140 – 840 g	

\* SILIKAL® Filler SL (contains no quartz powder) can be used instead of SILIKAL® Filler SV (line 2).

## 3. Self-levelling coating 4 – 7 mm

(Use in system D)

### Guideline recipe and batch quantities

Item	Component	Guideline recipe (% by weight)	Comments	Batch for 30 litre bucket	
1	SILIKAL® RV 368 resin	30 %		16 kg	16 litres
2	SILIKAL® Filler QM	20 %		10 kg	approx. 11 litres
3	SILIKAL® Filler SL	50 %	1 sack	25 kg	approx. 18 litres
	<b>Total:</b>	<b>100 %</b>	<b>Average consumption: 1.7 kg/m<sup>2</sup> per mm thickness</b>	<b>51 kg</b>	<b>approx. 30 litres</b>
4	SILIKAL® Hardening Powder	1 – 6 % related to item 1	See “Hardener dosages” table for quantities	160 – 960 g	

### Special advice:

Because of the high elasticity, no hard materials may be used as the overcoat. If a hard top coat is nevertheless required for reasons of resistance to chemicals, e. g. SILIKAL® R 72 resin, the surface must be pre-sealed with a semi-elastic intermediate sealant (e. g. SILIKAL® R 62 resin).

Extremely high spot stresses may result in slight indentations in the surface, but these are largely reversible.

# SILIKAL® RV 368 resin

Reactive, impact-resistant resin with low-temperature flexibility for self-levelling coatings



## Characteristics of RV 368 as delivered

Property	Measuring method	Approx. value
Viscosity at +20 °C	DIN 53 015	1000 mPa · s
Flow time at +20 °C, 6 mm cup	ISO 2431	135 – 165 sec.
Density D <sub>4</sub> <sup>20</sup>	DIN 51 757	0.98 g/cm <sup>3</sup>
Flash point	DIN 51 755	+10 °C
Pot life at +20 °C (100 g, 2 % pbw. hardening powder)		approx. 15 min.
Application temperature		+5 °C to +30 °C

## Characteristics of the self-levelling coating 4 – 7 mm

Property	Measuring method	Approx. value
Compressive strength	DIN 1164	25 N/mm <sup>2</sup>
Tensile strength in bending	DIN 1164	15 N/mm <sup>2</sup>
Specific weight		1.7 g/cm <sup>3</sup>

## Hardener dosages

Temperature	Hardening powder % pbw. *	Pot life approx. min.	Hardening time approx. min.
+5 °C	6.0	20	60
+10 °C	4.0	15	40
+15 °C	3.0	15	40
+20 °C	2.0	15	40
+25 °C	1.5	12	30
+30 °C	1.0	10	25

\* The quantity of hardening powder is always related to the quantity of resin.  
👁 For further information, please refer to the separate product information sheet "SILIKAL® Hardening Powder".



Other applicable documents	Data sheet	Page
SILIKAL® Additive ZA	SILIKAL® Additive I	84
SILIKAL® Hardening Powder	SILIKAL® Hardening Powder	86 – 87
General processing information	AVH	89 – 92
The substrate	DUG	93 – 95
Fillers and pigments	FUP	96 – 99
Chemical resistance	CBK	100 – 101
Information on safety and protection	SUS	102 – 103
Storage and transport	LUT	104 – 106
General cleaning advice	ARH	107 – 108

### Silikal GmbH & Co. KG

✉ Ostring 23  
☎ +49 (0) 61 82 / 92 35-0  
🌐 www.silikal.de

D-63533 Mainhausen  
☎ +49 (0) 61 82 / 92 35-40  
@ mail@silikal.de

### Silikal product information

Issue 2.00.A  
July 2006  
Data sheet SILIKAL® RV 368  
Page 3 of 3